

REZ-N-GLUE #1

PRODUCT CODE:

11C1 Rez-N-Glue #1

PHYSICAL PROPERTIES:

Viscosity: 2000 – 3000 cps
Solids: 39.3 – 41.3%
Density: 0.928 g/ml
Appearance: clear, water-white liquid
Shelf Life: 2 years unopened

PRODUCT DESCRIPTION AND USES:

Schwartz Rez-N-Glue #1 is a heavy-bodied adhesive suitable for polystyrene foam, fabric, and paper. It is also used in the arts and crafts industry as general-purpose glue.

PRODUCT ADVANTAGES:

1. Bonds a broad range of materials
2. High green tack
3. Clear bond line

ENVIRONMENTAL INFORMATION:

VOC: 554 g/L

APPLICATION DATA:

Suggested Uses: Used for bonding polystyrene foams, fabric, paper and other arts and crafts materials
Pot Life: NA
Reducer: NA
Retarder: NA
Clean-up Solvent: 4T002 or 4T003

DIRECTIONS FOR USE:

Surface Preparation: Surface to be bonded must be clean, dry and contaminant-free.

Dry Time: For maximum strength, do not disturb bond for 24 hours to allow complete cure.

CAUTION: Cold temperature, high humidity, or lack of airflow will prolong dry times.

Ambient Conditions: Use only when ambient conditions are 18°C to 30°C and RH= 40-60%.

Storage: Store indoor at room temperature, away from heat, ignition sources, open flames and direct sunlight.

Application: Apply adhesive on one surface to be bonded using brush or tongue depressor-type applicator. Bond while in wet condition. Allow to dry undisturbed for 1-2 hours. Be careful when handling bonded materials that has not been dried for 24 hours. Allow to completely cure for 24 hours to achieve maximum strength.

Warning: Use in a well-ventilated area. AVOID sparking, use non-sparking tools. Avoid open flames, turn off all pilot lights, ensure that work area is properly ventilated. Soiled rags and waste products may contain combustible liquids or vapours, dispose in accordance with local regulations. Refer to MSDS for information on safe use of this product.

LIMITATIONS and WARRANTY

The recommendations made and the information herein is based on our own and independent laboratory experience, and is believed to be accurate under controlled conditions. However, no warranty or guarantee of accuracy is made because we cannot cover every possible application of product nor anticipate every variation encountered in weather conditions, job- conditions, methods used and types of surfaces on which the product is applied. The users shall make their own tests to determine the suitability of such products for any particular purpose. Schwartz makes no warranties with respect to this product, expressed or implied, without limitation, the implied warranties of merchantability or fitness for a particular purpose.

Schwartz liability shall be limited in all events to supplying sufficient product to re-treat and/or repair the specific area to which Schwartz product has been applied. Schwartz reserves the right to have the true cause of any difficulty determined by accepted test methods. Schwartz shall have no other liability, including liability for incidental, consequential or resultant damages, however caused, whether due to breach of warranty, negligence, or strict liability.

THIS WARRANTY MAY NOT BE MODIFIED OR EXTENDED BY REPRESENTATIVES OF SCHWARTZ, ITS DISTRIBUTORS OR DEALERS.